



COLORS &
EFFECTS

BASF
We create chemistry

Xfast[®] for wood coatings

Stir-in pigment preparations for water-based transparent wood coatings

Key features

- Outstanding properties compared to dyes (e.g. light and weather fastness, no bleeding)
- Excellent color strength, gloss and transparency

Bonus features

- Dry granulate
- Low dust processing
- Outstanding dispersibility
- Combination with effect pigments offers endless styling opportunities

Xfast in wood coatings

- No need for milling
- Easily incorporated into a variety of water based systems with dissolvers or high-shear mixers
- Suitable for glazes and lacquers

Xfast® range for wood coatings


Wood shades with water-based coating

Xfast®	Color index	Chemistry	Pigment Content [%]
Yellow 1916	P.Y.42	Iron oxide hydrate, transp.	60
Red 2817	P.R.101	Iron (III) oxide, transp.	60
Green 8730	P. G. 7	Cu-phthalocyanine, halogenated	80
Black 0063	P.Bk.7	Carbon Black	70
White 0025	P.W.6	Titanium dioxide	85

Starting formulation with Xfast® for 100g glaze

Shade	Yellow 1916	Red 2817	Green 8730	Black 0063	White 0025
Scots pine	12.50				
Stone pine	5.97	0.30		0.01	
Oak	2.72	0.43		0.06	
Walnut	3.95	1.32		0.16	
Chestnut	1.13	1.98		0.07	
Teak	0.78	7.82		0.20	
Olive ash	9.45	0.48		0.30	
Rosewood		4.68		0.63	
Ebony				1.49	
Mahogany		7.67			
Fir Green	2.84		0.37	0.24	
Silver Grey	0.28			0.12	3.33

Wood shades



Common wood shades can be made by using these five products. Explore the Xfast® range for further color options...

Contacts

Asia Pacific

BASF Colors & Effects Shanghai Ltd.
No 300, Jiang Xin Sha Road
200137 Shanghai
China

EMEA

BASF Colors & Effects GmbH
An der Rheinschanze 1
67059 Ludwigshafen
Germany

Americas

BASF Colors & Effects USA LLC
24710 West Eleven Mile Road
Southfield, MI 48034
USA

Visit our website: www.colors-effects.basf.com

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. The agreed contractual quality of the product results exclusively from the statements made in the product specification. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed. When handling these products, advice and information given in the safety data sheet must be complied with. Further, protective and workplace hygiene measures adequate for handling chemicals must be observed. (07/2017)

® = Registered trademark of the BASF Group